ชื่อเรื่อง

: การทดลองเนื้อดินปั้นไส้กรองน้ำเซรามิก

ผู้วิจัย

: นายจุมพฏ พงศ์ศักดิ์ศรี

ที่ปรึกษา

: รองศาสตราจารย์วัฒนพงษ์ รักษ์วิเชียร

ประเภทวิทยานิพนธ์ : วิทยานิพนธ์ กศ.ม. (อุตสาหกรรมศึกษา) มหาวิทยาลัยนเรศวร, 2542

การทดลองเนื้อดินปั้นใส้กรองน้ำเซรามิก มีจุดมุ่งหมายเพื่อศึกษาทดลองเนื้อดินปั้นใส้ กรองน้ำเซรามิก จากส่วนผสมของ ไดอะทอไมท์ ดินชาวระนอง อะลูมิน่า โดโลไมท์ โดยมีผงถ่าน ละเอียดเป็นสารเพิ่มเติมทุกส่วนผสมร้อยละ 20 จะได้จำนวนส่วนผสมที่ต้องทดลอง จากตารางสี่ เหลี่ยมจัตุรัส 81 ส่วนผสม วิธีการดำเนินการวิจัยแบ่งออกเป็น 2 ขั้นตอน ดังนี้ ตอนที่ 1 ชั่งส่วน ผสมที่ได้จากตารางสี่เหลี่ยมจัตุรัส บดผสม ทำเป็นชิ้นทดลอง อบให้แห้งแล้วนำไปเผาที่อุณหภูมิ 800 850 900 950 1,000 1,050 องศาเซลเซียส ทดสอบคุณสมบัติทางกายภาพภายหลังการ เผาได้แก่ การดูดซึมน้ำ การหดตัวภายหลังการเผา คัดเลือกส่วนผสม ที่มีค่าการดูดซึมน้ำสูงสุด นำ ไปขึ้นรูปด้วยวิธีหล่อในพิมพ์ปูนปลาสเตอร์เป็นไส้กรองน้ำ ตอนที่ 2 ทดสอบประสิทธิภาพไล้กรองน้ำ ได้แก่ หาอัตราการกรองของน้ำที่ผ่านไส้กรองน้ำ วิเคราะห์คุณภาพน้ำ คุณลักษณะ สี ความขุ่น โดย ศูนย์อนามัยสิ่งแวดล้อมเขต 9 จังหวัดพิษณุโลก วิเคราะห์คุณภาพน้ำคุณลักษณะ กลิ่น โดย การสูดกลิ่น

จากการดำเนินการพดลองปรากฏผลดังนี้ ส่วนผสมที่มีค่าการดูดซึมน้ำมากที่สุดคือส่วน ผสมที่ 79 มีค่าการดูดซึมน้ำ ร้อยละ 78.30 ภายหลังจากการเผาที่อุณหภูมิ 850 องศาเซลเซียส มี ส่วนผสมคือ ไดอะพอไมท์ ร้อยละ 45 ดินขาวระนอง ร้อยละ 15 อะลูมิน่า ร้อยละ 35 โดโล ไมท์ ร้อยละ 5 ผงถ่านละเอียด ร้อยละ 20 ผลการพดสอบประสิทธิภาพไล้กรองน้ำตัวอย่างที่ได้ จากส่วนผสมที่ 79 เมื่อพดสอบที่ความดันน้ำ 15 ปอนด์/ตารางนิ้ว น้ำก่อนผ่านไล้กรองน้ำ มีค่า ความขุ่น 58.8 หน่วยเอ็นที่ยู และน้ำเมื่อผ่านไล้กรองน้ำแล้ว มีค่าสีน้อยกว่า 2 หน่วยแพลทินัม โคบอลต์ ค่าความขุ่น 0.2 หน่วยเอ็นที่ยู กลิ่นไม่เป็นที่รังเกียจ มีอัตราการกรอง เฉลี่ย 46.45 ลิตร/ขั่วโมง ที่ความดันน้ำ 40 ปอนด์/ตารางนิ้ว น้ำก่อนผ่านไล้กรองน้ำ มี ค่าสี 10 หน่วยแพลทินัม โคบอลต์ ค่าความขุ่น 10.37 หน่วยเอ็นที่ยู และน้ำเมื่อผ่านไล้กรองน้ำ ค่าสี 5 หน่วยแพลทินัม โคบอลต์ มีค่าความขุ่น 0.04 หน่วยเอ็นที่ยู กลิ่นไม่เป็นที่รังเกียจ มีอัตราการกรอง เฉลี่ย 100.65 ลิตร/ชั่วโมง ซึ่งเป็นไปตามมาตรฐานผลิตภัณฑ์อุตสาหกรรมไล้กรองน้ำเซรามิก เลขที่ มอก. 1420 – 2540

Title : AN EXPERIMENT OF CERAMIC WATER FILTER CANDLE BODY

Author : Mr. Jumpot Phongsaksri

ŵ,

Ę

Adviser : Assoc.Prof.Wattanapong Rakwichian

Type of Work: Thesis (M.Ed. in Industrial Education), Naresuan University 1999.

The purpose of the experiment was to study ceramic water filter candle body made from the mixture of diatomite, Ranong clay, alumina, dolomite and charcoal powder. Twenty percent of each material was mixed with fine carbon from the quadraxial diagram of 81 mixing substances. There were two stages in the study: Stage 1; weigh the substance according to the square diagram, ground and mixed them, made a sample piece, dried it and then burned it at 800, 850, 900, 950, 1,000, 1,050 degrees celcius, test its physical quality after burning, that is, water absorption and shrinkage. Stage 2: selected the subtance which was the most absorbent to be moulded in plaster cast and used as water filter, then tested its efficiency. The pore size was analysed by Thailand Institute of Scientific and Technological Research, the ratio of water filtering through this filter was analyed, had the quality, colour, and turbidity of the water analysed by the Sanitary Environment Center, Region 9, Phitsanulok, had the water smell analysed by five specialists. The study revealed that the mixture which could absorb the most water was the seventy-ninth mixture. It could absorb 78.30 % of water after burning at 850 degrees celcius. The subtances to be mixed were diatomite (45%), Ranong clay (15%), alumina (35%), dolomite (5%) and charcoal powder (20 %of the whole mixture). When tested under the water pressure of 15 lb/in², the water before going through the filter had turbidity of 58.8 ntu. After passing through the filter, the colour value was less than 2 platinum-cobalt turbidity of 0.2 ntu. The smell was satisfaction. The filtering rate was 46.45 litres per hour at the water pressure of 40 lb/in2. The water before passing through the filter had the colour value of 10 platinum-cobalt turbidity of 10.37 ntu. The water after passing through the filter had the colour value of 5 platinumcobalt turbidity of 0.04 ntu. The odor was satisfactary. The filtering rate was 100.65 litres per hour which was the standard of industrial products. of IS: 1420 - 2540 ceramic water filter candle.